



I. Product Description

CRC Blue RTV (Room Temperature Vulcanizing) Silicone Adhesive is the simple way to seal, protect, bond, insulate and waterproof. Superb for forming instant, custom-shaped gaskets, **Blue RTV Silicone** adheres to most materials used in the industrial, electrical, metalworking and construction industries. **Blue RTV Silicone** is specifically designed as a heavy-duty industrial gasket sealant.

II. Applications

Recommended and designed for a wide range of sealing, bonding, protection, and waterproofing in HVAC, electrical, construction, aviation, metal working and many more applications.

III. Features & Benefits

- **Seals, Bonds, Waterproofs and Protects.**
- **Cures at Room Temperature.** No special curing methods required.
- **Chemically Stable.** Shows little change in physical properties after exposure to sunlight (UV rays), rain, snow, ozone, temperature extremes and weathering.

IV. Physical Properties without propellant

Flash Point	Not Applicable	Boiling Point	Not Applicable
Odor	Slight vinegar odor	Solubility	None in water
Appearance	Blue	% Volatile	Not Determined
Vapor Density	>air	Specific Gravity	1.007
VOC Content (Fed)	29 g/L, <3%	Temperature range	-60°F to 450°F
Sara Title III, Sect. 313 Chemicals	No		500°F Intermittent
Prop 65	No	Propellant	Nitrogen

V. Specifications and Approvals

When fully cured and washed, CRC Blue RTV Silicone Adhesive meets the following regulations:

- TT-S-001543A Class A
- TT-S-00230C Class A
- ASTM C-920
- FDA regulation 21 CFR 177.2600

VI. Performance Characteristics

Cure Time (Total)	24 hours
Elongation Rate	500%
Dielectric Strength	550 volts/mil
Tensile Strength	350 psi
Durometer Hardness (Shore A)	30

VII. Directions

- Clean and dry all surfaces. Remove any oil and grease prior to application. Adhesive adheres best to clean, unpainted surfaces.
- For a smooth seal, hold the pressurized container at a 45° angle and apply adhesive by pressing finger to nozzle to tilt sideways.
- If further tooling is required, complete within 5 minutes. Remove excess adhesive immediately with a dry paper towel.
- Normally adhesive “skins” in 10 minutes, dries to the touch in one hour and fully cures and bonds in 24 hours.
- If gasket is not used in assembly, apply adhesive to surface of one part and allow skin to form before assembling parts.
- After adhesive is completely cured, excess material can be removed by trimming with a sharp blade. Avoid undercutting the adhesive.
- **Resealable:** If contents are not completely used, extrude 3/8” bead of adhesive beyond the tube opening. When ready to re-use, simply pull out the cured plug.
- Not recommended for use involving continuous immersion in gasoline or head gasketing operations.

VIII. Package Description

Part Number	Container Size
14057	8 oz Pressurized Tube

IX. Disposal

Disposal requirements vary by state and local jurisdiction. All used and unused product should be disposed of in conformance with local, state and federal regulations.

X. Special Use Warnings

Aerosol Cans

Do not puncture, incinerate or store above 120°F. Exposure to high temperatures may cause can to burst. Do not place in direct sunlight or near any heat source. Aerosol cans will conduct electricity. Keep away from all live electrical sources including battery terminals, solenoids, electrical panels and other electronic components. Failure to observe this warning may result in serious injury from flash fire and/or electrical shock.

General

Use only in well-ventilated area. Ventilation may be improved by opening a window or door or providing mechanical assistance. Avoid continuous breathing of vapor and spray mist. Avoid contact with skin and eyes. If ventilation is not adequate, respiratory protection should be worn. For more information regarding short term and long term exposure, review this product’s Safety Data Sheet.

DISCLAIMER: This information is accurate to the best of CRC Industries’ knowledge or obtained from sources believed by CRC to be accurate. Before using any product, read all warnings and directions on the label. All products should be tested for suitability on a particular application prior to actual use. CRC Industries, Inc. makes no representations or warranties of any kind concerning this data.

CRC Industries, Inc.
Technical Service: (800)521-3168

Industrial Products Division
Customer Service: (800)272-4620

Warminster, PA 18974
CRC On-Line: (215)442-6260